



ULTRA-HIDE®
Durus™ Acrylic
Exterior Flat Finish
GL 2210

Product Description

Our professional best exterior acrylic flat finish specially formulated to provide excellent mildew resistance, easy application and quick curing. Ideal for use on properly prepared wood siding, trim and sash, shakes, shingles, masonry, weathered aluminum siding, weathered vinyl siding, metal and sound painted surfaces.

Features

- Fade and chalk resistant
- Gives a mildew resistant coating
- Moisture-resistant
- Durable and tough
- Excellent adhesion
- Resists blistering, peeling and flaking
- Easy application
- Excellent touch-up
- Low odor
- Quick drying and recoat
- Low VOC
- Performance alternate for Federal Paint Specifications TT-P-19D and TT-P-96D

Composition

- 100% Acrylic Resin
- Titanium Dioxide and Extender Pigments
- Not manufactured with lead or mercury containing materials.

Specifications

Color:

White & custom colors

Finish:

Flat

Clean-up Solvent:

Soap and water

Density:

11.2 lbs/gal (1.34 kg/L)

VOC:

2.01 lbs/gal (241 g/L)

Solids:

Volume - 34% ± 1%

Weight - 52% ± 1%

Practical Coverage:

Apply at 300-400 sq ft/gal (7-10 m²/L). Actual coverage may vary depending on substrate and application method.

Flash Point:

None

Dry Time 77°F (25°C) & 50% RH:

To touch - 1 hour

To recoat - 4 hours

Shelf Life:

1 year minimum - unopened



General Surface Preparation

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, form release agents, curing compounds, loose and flaking paint and other foreign substances.

NEW SURFACES: Wood - Spot prime pine knots with Aquacrylic GRIPPER GL 3210. Prime entire surface with acrylic primer GL 2010. Caulk with latex-type caulk.

Preprimed and Unprimed Hardboard - Prime entire surface and all edges with acrylic primer GL 2010 or alkyd primer GL 2110. Caulk with latex-type caulk. **Steel** - Prime with waterborne metal primer or solventborne metal primer.

Galvanized Metal and Aluminum - Prime with acrylic primer GL 2010 or Aquacrylic GRIPPER GL 3210.

Concrete and Masonry - Cure at least 30 days before painting. pH must be 10.0 or lower. Roughen slick poured or precast concrete by acid etching or sandsweeping. Follow acid manufacturer's application and safety instructions. Rinse thoroughly with water and allow to dry. Remove loose aggregate. Prime with this product or acrylic primer GL 2010. Fill masonry block with latex block filler GL 3010.

PREVIOUSLY PAINTED SURFACES: Wash to remove contaminants. Rinse thoroughly with water and allow to dry. Dull glossy areas by light sanding. Remove sanding dust.

Remove loose paint. Scrub heavy chalk areas and overhead areas such as eaves with soap and water. Remove all mildew by washing with a solution of 16 oz (473 mL) liquid household bleach and two oz (59 mL) non-ammoniated liquid detergent per gallon (3.785 L) of water. Rinse surfaces clean with water and allow to dry for 24 hours. Prime bare areas with primer specified under **NEW SURFACES**.

Weathered Aluminum and Vinyl Siding - Remove dirt and chalk. Prime with this product. If chalk remains after cleaning, prime with acrylic primer GL 2010. Do not repaint vinyl siding with colors darker than the original color; the siding may warp.

NOTE: Blistering and peeling of exterior house paints down to bare wood is usually caused by moisture behind the paint film. Moisture pressure forces the paint away from the surface. Sources of excess moisture in the wood must be eliminated prior to repainting to obtain normal service life of these paints. Old, unsound multiple coat paint systems may be subject to peeling when repainted due to the added weight and stress created by the paint layers. In such cases, all old paint layers must be removed back to the bare wood before repainting.

Directions For Use

TINTING: Tint the appropriate base with universal colorants.

SPREADING RATE: Apply at 300-400 sq ft/gal (7-10 m²/L). Actual coverage may vary depending on substrate and application method. For best hiding, tint primers towards finish coat color. Certain shades of yellow, orange, pink and red may require multiple coats.

APPLICATION: Mix thoroughly before use. May be applied by brush, roller or spray. No thinning required.

For airless spray application, use .015" tip. Adjust pressure as needed. Do not apply when the surface or air temperature is below 50°F (10°C).

DRYING TIME: At 77°F (25°C) and 50% R.H., dries to touch in one hour and to recoat in four hours. Low temperature, high humidity, thick films or poor ventilation will increase these times.

CLEAN-UP: Clean immediately with warm, soapy water.

Precautions

WARNING! HARMFUL IF INHALED. MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS, INCLUDING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. OVEREXPOSURE MAY CAUSE LIVER, KIDNEY DAMAGE. HARMFUL IF SWALLOWED. CONTAINS ETHYLENE GLYCOL WHICH CAN CAUSE SEVERE KIDNEY DAMAGE WHEN INGESTED AND HAS BEEN SHOWN TO CAUSE BIRTH DEFECTS IN LABORATORY ANIMALS. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. For emergency information call (800) 545-2643. If sanding is done, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** In case of skin contact, wash off quickly with plenty of soap and water. For eye contact flush immediately with large amounts of water, for at least 15 minutes. Obtain emergency medical treatment. If swallowed, obtain medical treatment immediately. If inhalation causes physical discomfort, remove to fresh air. If discomfort or irritation persists, get medical help. **KEEP FROM FREEZING** Note: These warnings encompass the product series. Prior to use, read and follow product-specific MSDS and label information.

0244-0787

Shipping

FREIGHT CLASSIFICATION:

Paint, Freezable

PACKAGING:

1 gallon (3.785 L)
5 gallons (18.925 L)

FLASH POINT:

None



The Glidden Company, 925 Euclid Ave., Cleveland, Ohio 44115 1-800-GLIDDEN

LIMITATION OF LIABILITY To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.